



Eco Nitrile PF 250

Powder Free Extra Length Ambidextrous Non-Sterile 25 cm Nitrile Gloves with Textured Fingertips

Registered as PPE Category III (Complex Design) according to Council Directive 89/686/EEC

Fully compliant to the latest PPE norms - EN 374:2003 "Protective gloves against chemicals and micro-organisms"

PRODUCT INFORMATION

Size	Catalogue Numbers	Applicat	ograms	
Extra Small (XS/6)	62 5121	EN 374:2003	EN 374:2003	
Small (S/7)	62 5122			()
Medium (M/8)	62 5123		Level 3	0120*
Large (L/9)	62 5124	EN420:2003 + A1:2009		
Extra Large (XL/10)	62 5125	Also meets or exceeds EN 455-1:2000, EN 455-2:2015, EN 455-3:2015 & EN 455-4:2009 relating to Council Directive 93/42/EEC for Medical Devices		

* SGS UK Ltd (Notified Body No: 0120), Unit 202B Worle Parkway, Weston-super-Mare, BS22 6WA, United Kingdom

- Material: Synthetic soft nitrile polymer (Acrylonitrile Butadiene), based on twinSHIELD™ technology. Contains no natural rubber latex.
- **Design:** Double barrier protection afforded by green outer layer, combined with white inner lining. Ambidextrous, beaded cuff and with textured fingertips.
- Packaging: Hundred & fifty (150) gloves per natural carton dispenser. Gloves are flat-packed. Ten (10) dispensers per case. Recycle carton only.

PHYSICAL PROPERTIES

Characteristics	Value			Test Method
Freedom from holes	<0.65 AQL ¹			EN 374:2003
¹ AQL as defined per ISO 2859 for san Tensile Properties	Tensile Strength (min) Typical Elonga			
- Before Aging	6.0N, min.	7.0N	500%, min.	EN 455-2:2015, ASTM D573-04(2015) and ASTM D 412-15a
- After Accelerated Aging	6.0N, min.	8.0N	400%, min.	

Dimensional	Measured Point	Mm	mil	
- Nominal Thickness	Middle Finger	0.14	5.5	ASTM D3767-03(2014)
	Palm	0.10	3.9	
	Cuff	0.08	3.0	
- Length XS/6-L/9 XL/10	250mm, min. 260mm, min.		255mm, typical 265mm, typical	EN 420:2003 + A1:2009

Palm Widths	1					
- Nominal Width (mm)	XS/6	S/7	M/8	L/9	XL/10	EN 455-2:2015
	≤80	85	95	105	≥110	
Hand Circumference	1					
- Nominal circumference	XS/6	S/7	M/8	L/9	XL/10	EN 420:2003 + A1:2009

ADDITIONAL DATA

152

1472 141

(mm)

• Biocompatibility demonstrated by Modified Buehler and Primary Skin Irritation Tests.

203

178

• Non-detectable levels of chemical allergens using aqueous solution extraction (Phosphate buffered solution) and High Performance Liquid Chromatography (HPLC) assay method for quantitative analysis.

229

254

- Free of Thiazoles and Thiurams these chemical accelerators are excluded from the manufacturing process.
- **Powder free** to minimize the potential consequences of powder-borne dermatitis. Residual powder content is 1.0 mg/glove (typical) with a limit of 2.0 mg/glove (ISO 21171:2006 "Medical gloves Determination of removable surface powder").
- Micro organism and virus resistant passes highest level of micro organism resistance per EN 374-2:2014 (Performance level 3, AQL <0.65 and inspection level G1 according to 1000ml water test) and passes viral penetration test using Phi-X 174 bacteriophage (ISO 16604:2004 Procedure B & ASTM F1671-97b).
- Ecological 50% more products in the same volume to limit CO2 emissions and save space storage. Ink on the packaging reduced by 60%. Packaging made from recycled cardboard. Supply Chain optimized to reduce CO2 emissions by more than 15% to deliver our products.
- Extensively tested for chemical permeation according to EN 16523-1:2015 (please refer to chemical resistance guide on website www.shieldscientific.com/public/chemical-resistance-guide).

QUALITY SYSTEMS

• Manufactured in accordance with ISO 9001:2015 and ISO 13485:2016.

"ecoSHIELD™, Protect Your Future"



www.shieldscientific.com

ecoSHIELD[™] and twinSHIELD[™] are trademarks of SHIELD Scientific. © 2007 Copyright SHIELD Scientific B.V. - All Rights reserved 2007 Copyright SHIELD Scientific B.V. - All Rights reserved Dr. Willem Dreeslaan 1 ∘ 6721 ND Bennekom ∘ The Netherlands - Phone +31 (0)317 700 202 ∘ Fax +31 (0)318 503 742 ∘ E-mail: Info@shieldscientific.com